



Technical Data Sheet

Commercial 3A Modified

Gradation	
US Standard Mesh	% Passing
#16	13.7
#8	22.6
#4	33.1
3/8"	48.1
3/4"	72.4
1"	81.9
3"	100.00

Proctors			
Standard		Modified	
Proctor	Moisture	Proctor	Moisture
142.2	6.9	145.9	4.8

