



Technical Data Sheet

Crushed Concrete

Gradation	
US Standard Mesh	% Passing
3/8"	55.0
1/2"	63.5
3/4"	87.0
1"	95.5
1 1/2"	98.5
2"	100.0
WASH	7.50

Properties	
Density Loose lbs/cu.ft	87.97
Density Rooded lbs./cu.ft	107.37
Standard Proctor	
Proctor	Moisture
140.4	8.3

